## PRODUCT SPECIFICATION AND TYPICAL RESULT CHASSIS GREASE No.2 (DG-502)

Test	Method	Specification	Typical Result
NLGI Grade Thickener Type Texture Color Penetration at 25 °C (Worked 60-Strokes), mm Penetration at 25 °C (Un Worked), mm Dropping Point, °C Water Washout at 79 °C, % washout Base Oil Viscosity Kinematics at 100 °C, cSt.	- Visual ASTM D 217 ASTM D 217 ASTM D 2265 ASTM D1264 ASTM D 445	2 Calcium Smooth & Tacky Dark Green 265-295 Report Min.90 Max.10 15 -18	2 Calcium Smooth & Tacky Dark Green 275 272 108 2.01 17.45

